



NFRC Ratings - Thermal Aluminum T225 Door

Glass values are based on Aluminum Spacer

Argon gas cannot be ordered for projects located above 4,000 ft. elevation; breather tubes required.

IGU Thickness	Grid	Glass Type	Pane 2	Pane 3	Gap 1	Gap 2	Fill	U_VALUE	SHGC	VT	CPD #
1" Dual Glazed	N	Cardinal LoE-366	i89		0.5		ARGON	0.36	0.21	0.45	SOD-K49-00015-00001
1" Dual Glazed	S	Cardinal LoE-366	i89		0.5		ARGON	0.44	0.18	0.39	SOD-K49-00016-00001
1" Dual Glazed	N	Cardinal LoE-366	CLEAR		0.5		ARGON	0.41	0.21	0.46	SOD-K49-00013-00001
1" Dual Glazed	S	Cardinal LoE-366	CLEAR		0.5		ARGON	0.54	0.19	0.4	SOD-K49-00014-00001
1" Dual Glazed	N	SN68	CLEAR		0.5		ARGON	0.41	0.28	0.5	SOD-K49-00011-00001
1" Dual Glazed	S	SN68	CLEAR		0.5		ARGON	0.54	0.25	0.43	SOD-K49-00012-00001
1" Dual Glazed	N	SN68	CLEAR		0.5		AIR	0.44	0.29	0.5	SOD-K49-00009-00001
1" Dual Glazed	S	SN68	CLEAR		0.5		AIR	0.56	0.26	0.43	SOD-K49-00010-00001